



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 5 : C10G 11/22, C07C 5/48	A1	(11) International Publication Number: WO 94/04632 (43) International Publication Date: 3 March 1994 (03.03.94)
(21) International Application Number: PCT/GB93/01741 (22) International Filing Date: 17 August 1993 (17.08.93) (30) Priority data: 9217685.8 20 August 1992 (20.08.92) GB (71) Applicant: BP CHEMICALS LIMITED [GB/GB]; Britan- nic House, 1 Finsbury Circus, London EC2M 7BA (GB). (72) Inventors: ASTBURY, Christopher, John ; 64B Brookwood Road, Southfields, London SW18 5BY (GB). GRIF- FITHS, David, Charles ; 110 Summer Road, Thames Ditton, Surrey KT7 0QP (GB). REID, Ian, Allan, Beat- tie ; 12 Crowthorne Close, Southfields, London SW18 5RX (GB).		(74) Agent: PREECE, Michael; BP International Limited, Pa- tents & Agreements Division, Chertsey Road, Sunbury- on-Thames, Middlesex TW16 7LN (GB). (81) Designated States: AU, BG, BR, CA, CZ, FI, HU, JP, KR, NO, NZ, PL, RO, RU, SK, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>
(54) Title: PROCESS FOR THE PRODUCTION OF MONO-OLEFINS (57) Abstract A process for the production of mono-olefins from a hydrocarbon feed containing one or more paraffinic hydrocarbons having at least two carbon atoms, the process comprising partial combustion of a mixture of the hydrocarbon feed and a molecular oxygen-containing gas in contact in a reaction chamber with a catalyst capable of supporting combustion beyond the normal fuel rich limit of flammability to produce heat of reaction, the reaction chamber being adapted such that at least part of the heat of reaction is transferred to the incoming feed and the velocity of the incoming feed is maintained at a value above the burning velocity of the feed mixture.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FR	France	MR	Mauritania
AU	Australia	GA	Gabon	MW	Malawi
BB	Barbados	GB	United Kingdom	NE	Niger
BE	Belgium	GN	Guinea	NL	Netherlands
BF	Burkina Faso	GR	Greece	NO	Norway
BG	Bulgaria	HU	Hungary	NZ	New Zealand
BJ	Benin	IE	Ireland	PL	Poland
BR	Brazil	IT	Italy	PT	Portugal
BY	Belarus	JP	Japan	RO	Romania
CA	Canada	KP	Democratic People's Republic of Korea	RU	Russian Federation
CF	Central African Republic	KR	Republic of Korea	SD	Sudan
CG	Congo	KZ	Kazakhstan	SE	Sweden
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovak Republic
CM	Cameroon	LU	Luxembourg	SN	Senegal
CN	China	LV	Latvia	TD	Chad
CS	Czechoslovakia	MC	Monaco	TC	Togo
CZ	Czech Republic	MG	Madagascar	UA	Ukraine
DE	Germany	ML	Mali	US	United States of America
DK	Denmark	MN	Mongolia	UZ	Uzbekistan
ES	Spain			VN	Viet Nam
FI	Finland				

PROCESS FOR THE PRODUCTION OF MONO-OLEFINS

The present invention relates to a process for the production of mono-olefins.

Olefins such as ethylene and propylene are extremely valuable industrial products both as monomers for homo- and co-polymer
5 production and as a basic starting material for the production of other desirable chemicals. Such olefins may be obtained through various processes which include the steam cracking of hydrocarbons such as naphtha and liquid petroleum gas feedstocks or through the dehydrogenation of paraffinic hydrocarbons.

10 European patent application 0332289 discloses a method for the production of mono-olefins which involves the partial oxidation of paraffinic hydrocarbons. Gaseous paraffinic hydrocarbons are mixed with a molecular oxygen-containing gas and contacted with a catalyst capable of supporting combustion beyond the fuel rich limit of
15 flammability. The process, hereinafter described as autothermal cracking provides an efficient and cost-effective method of producing mono-olefins with yields being in excess of that obtained through the conventional steam cracking technology.

The aforementioned process is successful for gaseous
20 hydrocarbon feeds such as ethane, propane or butane. The process is equally applicable to liquid hydrocarbons such as naphtha, gas oil or vacuum gas oil. The liquid hydrocarbons, however, are commonly preheated and partially vaporised prior to entering the reaction chamber, thus requiring an additional step in the process. A problem
25 associated with vaporisation of liquid hydrocarbons is that the

conditions, e.g. high temperature, required to achieve vaporisation of heavier feeds may cause cracking of the hydrocarbons. Additionally, complete vaporisation is difficult to achieve and consequently a fine film of liquid can form on the catalyst which can
5 reduce catalyst activity.

Attempts to overcome the aforementioned problem fall into two general categories. Firstly, additional oxygen may be used to promote the combustion and to raise the temperature of the catalyst. This, however, results in a decrease in the yield of olefins.
10 Alternatively, greater heat may be applied. In addition to the problem of cracking of the hydrocarbons, additional pre-heat may result in flashback or autoignition generating a flame at the fuel/oxygen mixing point. This type of flame generates very high flame temperatures and may result in carbon formation and thus a
15 decrease in the yield of olefins.

We have now developed a method for the production of mono-olefins using partial oxidation of hydrocarbons which can successfully convert both gaseous and liquid paraffinic hydrocarbons. Liquid hydrocarbons can be fed directly into the reactor wherein the
20 heat from the subsequent reaction pre-heats and at least partially vaporises the liquid prior to contact with the combustion catalyst.

Accordingly, the present invention provides a process for the production of mono-olefins from a hydrocarbon feed comprising one or more paraffins having at least two carbon atoms, the process
25 comprising partial combustion of a mixture of the hydrocarbon feed and a molecular oxygen-containing gas in contact in a reaction chamber with a catalyst capable of supporting combustion beyond the normal fuel rich limit of flammability to produce heat of reaction, the reaction chamber being adapted such that at least part of the
30 heat of reaction is transferred to the incoming feed, and the velocity of the incoming feed is maintained at a value above the burning velocity of the feed mixture.

The present invention provides the advantage that the mono-olefinic hydrocarbons may be produced more efficiently through the
35 autothermal cracking of either gaseous or liquid paraffinic

hydrocarbons. The process of the present invention is particularly suitable for liquid hydrocarbons. Heat generated within the reaction chamber by combustion of a proportion of the hydrocarbon feed is sufficient to support the cracking reactions thus eliminating the need for external heating supplies. Additionally, in the present invention, the arrangement of the reactor permits excess heat generated within the catalyst bed to pass through the wall of the reaction chamber to the inlet zone, thus heating and/or vaporising the incoming feed.

The process of the present invention assists the vaporisation of liquids which boil above the autoignition temperature without causing a flashback to or autoignition at the mixing point. The hydrocarbon feed and oxygen containing gas are introduced into the reactor at a temperature below the autoignition temperature and fuel-oxygen mixing takes place. The heat of the reaction from the catalyst zone heats the feed mixture and vaporises a significant fraction of the liquid feed before the mixture reaches the catalyst.

Conventionally, autothermal cracking is carried out by combustion of a hydrocarbon and an oxygen containing gas. With gas and liquid feeds, a sufficient amount of oxygen is required to maintain stable reaction conditions. In particular with liquid feeds, the temperature of the catalyst must be maintained at a level to ensure sufficient vaporisation of residual liquid from the catalyst surface to prevent reduction of catalyst activity. This ability depends on the heat transfer efficiency within the reactor. The process of the present invention also utilises combustion of hydrocarbon and oxygen containing gas. Additionally, heat transfer from the reaction zone to the incoming reactants is improved, having the advantage that the amount of unvaporised liquid hydrocarbon reaching the catalyst is minimised, reducing loss of activity. Thus, for liquid feeds, an additional vaporising step is not necessary since these may be fed directly into the reactor, the heat of reaction being sufficient to fully, or at least partially, vaporise the liquid hydrocarbons in situ. A further advantage is therefore that a greater proportion of hydrocarbon may be fed into the reactor

in liquid form without extinguishing catalyst activity. Furthermore, less oxygen is required to maintain stable reaction conditions, in particular the catalyst bed temperature and thus the process may be operated at a greater hydrocarbon to oxygen ratio. Consequently, less of the hydrocarbon is required to undergo combustion to generate heat for the cracking reactions, with the additional advantage that concentrations of carbon oxides in the product stream are reduced.

The process of the present invention is carried out in a reactor having a reaction chamber entered through an inlet zone and exited through an outlet zone. The reaction chamber accommodates a catalyst which is capable of supporting flammability. Suitably the reaction chamber surrounds or is surrounded by the inlet zone such that there is a common wall between both zones enabling the transfer of the heat of the reaction from the catalyst bed to the reactants. Alternatively, the reaction chamber may be situated at the end of the inlet zone, the incoming feed being pre-heated or vaporised as it enters the chamber. It is preferred that the walls of the reaction chamber and the inlet zone are arranged in concentric circles. In a preferred embodiment of the reactor suitable for use in the process of the present invention, the inlet zone will form a tube or central channel running through the centre of the reaction chamber and opening into the catalyst chamber at the end of the reactor opposite to the reactant inlet. Alternatively, the walls of the inlet zone and the reaction chamber may be arranged to form parallel adjacent channels, again there being a common wall between the two zones. It is preferred that the gases passing through the inlet zone and the reaction chamber move in mutually opposed directions.

The reactor of the present invention may comprise a single reaction chamber or may comprise a multiplicity of reaction chambers, the reaction chambers being arranged in a matrix.

The process of the present invention is for the production of mono-olefins from a hydrocarbon feed comprising paraffins. The feed may comprise gaseous hydrocarbons, liquid hydrocarbons or a mixture thereof. The process is especially suitable for liquid hydrocarbons. Suitable gaseous hydrocarbons are ethane, propane, butane, or

mixtures thereof. Suitable liquid hydrocarbons may include paraffin containing hydrocarbons such as naphtha, gas oil, vacuum gas oil refinery residues, atmospheric residues, vacuum residues or mixtures of liquid hydrocarbons as found in crude or fuel oils.

5 Additional feed components may be included, if so desired. In particular, hydrogen may be fed with the hydrocarbon feed into the reaction chamber. The presence of hydrogen usually enables enhanced yields of olefins and reduces the formation of carbon dioxide and carbon monoxide. It will of course be understood that the effect of
10 hydrogen will vary with the hydrocarbon feed. Additional gases such as carbon dioxide, methane, nitrogen, carbon monoxide or steam may be co-fed into the reactant stream.

Where the hydrocarbon feed is a liquid hydrocarbon, the feed may be passed directly into the reactor in the liquid state. The
15 feed may be pre-heated if desired. Suitably, the additional co-fed gases such as hydrogen are mixed with the liquid feed. Suitably, the mixture is introduced into the reaction chamber as a fine spray of droplets such that vaporisation and homogeneous mixing may result. Any suitable means may be used for providing a fine spray of liquid.
20 Suitably, the liquid may be passed through a nozzle. The size of the liquid droplets is suitably small to provide a fine spray of liquid. It will of course be understood that small droplets provide a more efficient vaporisation.

Suitably, the liquid hydrocarbon spray is directed towards the
25 reaction chamber. The heat generated within the catalyst by the partial combustion of the hydrocarbon, the oxygen containing gas and, if desired, hydrogen gas, is transferred through the walls of the chamber to cause heating and vaporisation of the atomised liquid hydrocarbon and heating of the feed.

30 The hydrocarbon feed is mixed with a molecular oxygen-containing gas. Suitably, the gas is oxygen, optionally diluted with an inert gas such as nitrogen. It is preferred to pre-mix the oxygen-containing gas and the paraffinic feed prior to contact with the catalyst. Suitably the amount of oxygen required for the process
35 of the present invention is from 2 to 20%, preferably 4 to 20% of the

amount required for complete combustion to carbon dioxide and water.

The velocity of the hydrocarbon and oxygen-containing gas mixture entering the reaction chamber must be maintained at a value above the burning velocity of the feed mixture. This is especially applicable to flammable mixtures i.e. a feed mixture which can propagate a flame freely within a limited range of compositions. It will of course be understood by the person skilled in the art that the gas velocity will vary for different hydrocarbon feeds, pre-heat temperature and stoichiometry. Typically, the velocity of the feed mixture may be suitably greater than 0.5ms^{-1} , preferably greater than 1ms^{-1} . For the purposes of the present invention, velocity is the velocity of the gas through the inlet zone and burning velocity is defined as the measure of unburnt gas velocity at the point of first temperature rise in a flame, perpendicular to the flame front.

The hydrocarbon feed and oxygen-containing gas is contacted with a catalyst which is capable of supporting combustion. The principle role of the catalyst is to stabilise partial combustion of the gaseous mixture which may not otherwise be flammable.

Suitably, the catalyst is a supported platinum group metal. Preferably, the metal is either platinum or palladium or a mixture thereof. Although a wide range of support materials are available, it is preferred to use alumina as the support. The support material may be in the form of spheres, other granular shapes or may be a continuous multichannel ceramic structure, eg a foam. A preferred support for the catalyst is a gamma alumina coated lithium aluminium silicate foam. The support is loaded with a mixture of platinum and palladium by conventional methods well known to those skilled in the art. The resulting compound is then heat treated to 1200°C before use in the process of the present invention. Optionally the compound may be reduced prior to use as a catalyst. It is preferred to use the catalyst as a fixed bed.

The process of the present invention may suitably be carried out at a temperature of greater than 600°C , preferably greater than 700°C , especially in excess of 750°C . The upper temperature limit may be suitably 1200°C , preferably 1100°C , especially 1000°C .

The hydrocarbon feed and the oxygen-containing gas may be pre-heated prior to contact with the catalyst. Where the paraffinic hydrocarbon is a gaseous paraffin such as ethane or propane, the gases may be suitably preheated to 200-500°C either prior to mixing with the oxygen-containing gas or after mixing. Where the paraffinic hydrocarbon is a liquid, the hydrocarbon may be heated prior to mixing with the molecular oxygen containing gas.

The gaseous feed mixture may be introduced into the reaction chamber under a gas hourly space velocity of suitably greater than 3000 hr⁻¹ in order to minimise the formation of carbon oxides. Preferably, the gas hourly space velocity exceeds 10000 hr⁻¹, especially greater than 100000 hr⁻¹. It will of course be understood that the optimum gas hourly space velocity will depend upon the feed and the pressure. For the purposes of the present invention, gas hourly space velocity is defined as:

$$\text{GHSV} = \frac{\text{volume of total feed at NTP}}{\text{Time} \times \text{volume of catalyst bed}}$$

The process may be carried out under atmospheric or elevated pressure. Where it is desired to use elevated pressure, suitably up to 30 bar, preferably up to 40 bar, most preferably up to 50 bar, it is preferred that the reaction products be quenched as they emerge from the reaction chamber to avoid further reactions taking place. Suitably, the reaction products are quenched within 50 milliseconds of formation. It will of course be understood that the time required for quenching the products will depend upon the reaction conditions such as temperature and pressure.

Where elevated pressure is employed, the reaction products may be quenched using rapid heat exchangers of the type familiar in steam cracking technology. Also possible, either additionally or instead of the indirect heat exchangers, a direct quench may be suitably employed. Suitable quenching fluids include water and hydrocarbons. At the aforementioned temperature and pressure, some of the hydrocarbon quenching fluid may be cracked to provide additional olefinic products in the effluent stream. Such hydrocarbon quenching fluids are referred to as reactive quenching fluids. The amount of

quenching fluid and choice of fluid which may be usefully employed will depend upon the temperature of the effluent stream. Optionally, a second quenching fluid such as water may be employed if a hydrocarbon fluid is utilised in the process.

5 The products of the process of the present invention are suitably ethene, propene, butenes and pentenes. In addition to these products, carbon monoxide, aromatic hydrocarbons as well as small amounts of methane, acetylenes, water, hydrogen and carbon dioxide may be produced. The products from the process of the present
10 invention are preferably removed from the reaction chamber rapidly by a high gas flow.

The invention will now be described by way of example with reference to Figures 1 and 2 and the following examples.

Figure 1 shows a vertical section through a reactor for
15 producing mono-olefins according to the present invention. Reactant feed is fed through an external inlet (1) and passed through a nozzle (2) into an inlet zone (3) surrounded by a reaction chamber (4) which accommodates a combustion catalyst. Products exit the reactor through an outlet zone (5) which is in the form of an annulus between
20 the outer wall (6) of the reaction chamber (4) and the outer wall (7) of the reactor. The reaction chamber (4) is in the form of a cylinder with the inlet zone (3) located in the inner annulus.

In use, the paraffinic hydrocarbon and oxygen are fed into the reactor through inlet (1). The reactants may be mixed either before
25 or after passage through the nozzle (2) into the inlet zone (3). Heat generated from reaction in the catalyst bed is transferred through the common wall (8) to the inlet zone, thus heating the incoming reactants and at least partially vaporising the liquid hydrocarbons. The reactants are then carried through the inlet zone
30 into the reaction chamber for cracking.

Figure 2 shows a vertical section through an alternative embodiment. Reactant feed is fed through an external inlet (9) and passed through a nozzle (10) into an inlet zone (11) which precedes the reaction chamber (12) which accommodates the combustion catalyst.
35 Products pass out of the reaction chamber (12) through an outlet zone

(13) which is in the form of annular channels between the outer wall (14) of the reaction chamber (12) and the outer wall (15) of the reactor.

In use, the paraffin containing hydrocarbon and oxygen are fed into the reactor through inlet (9). The reactants may be mixed either before or after passage through the nozzle (10) into the inlet zone (11). Products are carried out of the reaction chamber (12) through an outlet zone (13). A portion of the heat contained in the product gas is transferred through wall (14) to heat the incoming feed.

Example A - Preparation of Catalyst

The lithium aluminium silicate foam support was obtained precoated with gamma alumina from Morgan Matroc plc. with a porosity of 30ppi. The foam was washed with a platinum/palladium solution of tetraamine metal chloride salt, drawn through the support by vacuum, dried and finally calcined at 1200°C for 12 hours. The impregnation of the foam was controlled by monitoring the volume of solution absorbed by the foam to give a loading of 0.25wt% in the final catalyst.

Example B - Start-up Procedure at Atmospheric Pressure

The following start-up procedure is employed when using a liquid feed which contains sulphur compounds. At low temperatures, sulphur compounds in a feed can poison the catalyst surface and prevent the reaction taking place. By initiating the reaction with a sulphur free feed such as ethane, the catalyst temperature is raised to a level where sulphur does not poison the catalyst.

The Pt/Pd loaded ceramic foam catalyst was packed into the reaction chamber of the reactor. Ethane (1.71 litres per minute), hydrogen (1.8 litres per minute) and nitrogen (4 litres per minute) were passed into the reactor. Nitrogen was added as an internal standard for subsequent product analysis by gas chromatography and is not required for operation of the process of the present invention. Oxygen was added gradually until the catalyst temperature was seen to rise and continued until the nominal operating temperature of 900°C was reached. Ethane flow was then increased and if necessary, oxygen

flow increased to maintain the operating temperature. When the gas flows through the reactor were sufficiently high (greater than 10 litres per minute), the temperature was allowed to equilibrate.

Example C - Start-up Procedure at Elevated Pressure

5 The following start-up procedure is employed for the process when using a liquid feed containing sulphur compounds and when carried out at elevated pressure. The Pt/Pd loaded ceramic foam catalyst was packed into the reaction chamber of the reactor. The pressure in the reactor was increased to 5 bar(g) with nitrogen.
10 Ethane (20 litres per minute), hydrogen (16 litres per minute) and nitrogen (21 litres per minute) were passed into the reactor. Nitrogen was added as an internal standard for subsequent product analysis by gas chromatography and is not required for operation of the process of the present invention. Oxygen was added gradually
15 until the catalyst temperature was seen to rise and the oxygen, nitrogen and ethane flows were increased to give a catalyst temperature of approximately 750°C, at the preferred gas velocity. The temperature was allowed to equilibrate and optionally hydrogen was removed.

20 Example 1 - Ethane/Vacuum Gas Oil Feed

 When the operating temperature had reached equilibrium as outlined in Example B, a small amount of liquid hydrocarbon (vacuum gas oil) was introduced into the reactor and passed through the nozzle. Ethane and oxygen flows were altered to maintain the
25 required catalyst temperature. The liquid flow was then increased until the required feed rate and temperature were reached. The gas hourly space velocity was 19000 hr⁻¹ and oxygen concentration was approximately 4.5% of the amount of oxygen required for complete combustion to carbon dioxide and water, the process was operated at
30 atmospheric pressure.

 Samples were extracted at temperatures of 764°C and 700°C and product analyses are shown in Table 1. Carbon/oxygen molar ratios of 2 and 2.6 respectively were required to achieve these temperatures, representing very fuel rich mixtures. Selectivity to olefins of
35 47.7wt% and 41.9wt% respectively were obtained.

Example 2 - Vacuum Gas Oil Feed

The procedure of Example 1 was repeated until no ethane was present and vacuum gas oil was the sole hydrocarbon feed. The oxygen flow in this example was 12.8% of the amount required for complete combustion. A sample was extracted at 875°C and product analysis is also given in Table 1. Selectivity to olefin for the liquid hydrocarbon feed is 43.8wt%.

Example 3 Naphtha Feed

When the operating temperature had reached equilibrium as outlined in Example C, a small amount of liquid hydrocarbon (naphtha) was introduced into the reactor and passed through the nozzle at a rate of 39 grams per minute. Ethane and oxygen flow were adjusted to maintain the required catalyst temperature. Ethane was gradually removed and the naphtha flow increased to 49.2 grams per minute while the oxygen flow was adjusted to maintain the catalyst temperature at the required level. The reactor pressure was maintained at 5 bar(g). A sample was extracted at a catalyst temperature of 805°C under conditions detailed in Table 2. Selectivity to olefinic products was 42 wt%.

Comparative Example 1

The procedure of Example 1 was repeated for an ethane/vacuum gas oil feed using the autothermal cracking technology of European Application No. 0332289. The reactor contained the same catalyst as that of the reactor of the present invention (Pt/Pd loaded alumina washcoated lithium aluminium silicate foam) and was operated at a catalyst temperature of 767°C and 711°C. The process was operated at atmospheric pressure. Feed and product analyses are shown in Table 3. Carbon to oxygen ratio for the process using the reactor as described in EP-A-0332289 were 1.2 and 1.3 thus indicating the conventional reactor requires relatively fuel lean mixtures to maintain a similar catalyst temperature. Temperatures of approximately 880°C were measured above the catalyst. Olefin selectivity in this example was determined to be 34.8 and 37.2 wt%.

It can therefore be seen that olefin selectivities for the process of the present invention are higher for liquid hydrocarbon

feed and over a more extensive range of stoichiometries than for the known autothermal cracking process.

5

10

15

20

25

30

35

Table 1

Feed (g/min)				C ₂ /OIL	C(total) /O ₂	H/C	[†] Max Temp (°C)	Conversion (% mol)		Yield (wt%C)				
VGO	C ₂ H ₆	O ₂	N ₂	H ₂				*Ethane	*Oxygen	Olefins	Alkanes **	Aromatics	CO + CO ₂	
5.3	10.3	6.4	4.0	0.2	1.8	2.0	2.7	63.1	99.3	47.7	5.8	1	17.9	
5.3	10.3	5.0	4.0	0.2	1.8	2.6	2.7	46.8	98.5	41.9	5.1	2.0	14.9	
4.5	-	2.8	20.2	0.2	-	1.4	2.3	-	93.9	43.8	9.1	27.4	13.5	

Table 2

Feed (g/min)					C ₂ /OIL	C(total) /O ₂	H/C	[†] Max Temp (°C)	Conversion (% mol)		Yield (wt%C)				
Naphtha	C ₂ H ₆	O ₂	N ₂	H ₂					*Ethane	*Oxygen	Olefins	Alkanes **	Aromatics	CO + CO ₂	
49.2	0	24.4	52.1	0	-	1.7	2.2	805	-	99.2	42	15.9	0.6	20.1	

*Conversion = ethane in x 100%, oxygen in x 100%
ethane out oxygen out

[†]Maximum Temperature measured above the catalyst bed

**Ex ethane

Table 3

Feed (g/min)				C ₂ /OIL	C (total) /O ₂	H/C	[†] MaxTemp	Conversion (%) mol)		Yield (wt%)			
VGO	C ₂ H ₆	O ₂	N ₂	H ₂			(°C)	*Ethane	*Oxygen	Olefins	Alkanes **	Aromatics	CO + CO ₂
2.3	7.1	6.4	3.9	0.2	2.8	1.2	883	96.0	96.8	34.8	8.3	3.4	22.8
3.7	7.9	7.4	4.0	0.2	2.0	1.3	880	92.3	96.8	37.2	7.8	5.3	22.2

*Conversion = $\frac{\text{ethane in} \times 100\%}{\text{ethane out}}$, $\frac{\text{oxygen in} \times 100\%}{\text{oxygen out}}$

**Ex ethane

[†]Maximum Temperature measured above the catalyst bed

Claims

1. A process for the production of mono-olefins from a hydrocarbon feed comprising one or more paraffins having at least two carbon atoms, the process comprising partial combustion of a mixture of the hydrocarbon feed and a molecular oxygen-containing gas in contact in
5 a reaction chamber with a catalyst capable of supporting combustion beyond the normal fuel rich limit of flammability to produce heat of reaction, the reaction chamber being adapted such that at least part of the heat of reaction is transferred to the incoming feed, and the velocity of the incoming feed is maintained at a value above the
10 burning velocity of the feed mixture.
2. A process according to claim 1 in which the reaction chamber surrounds or is surrounded by an inlet zone such that there is a common wall between said chamber and zone.
3. A process according to claim 2 in which the reaction chamber
15 and the inlet zone are arranged concentrically.
4. A process according to claim 2 in which the inlet zone and reaction chamber are arranged to form parallel adjacent channels.
5. A process according to any one of the preceding claims in which the hydrocarbon feed is a liquid paraffinic hydrocarbon.
- 20 6. A process according to claim 5 in which the hydrocarbon feed is naphtha, gas oil, vacuum gas oil, refinery residues, atmospheric residues, vacuum residues or mixtures of liquid hydrocarbons as found in crude or fuel oils.
7. A process according to any one of the preceding claims in which
25 the catalyst is a platinum group metal on a support.

8. A process according to claim 7 in which the support is alumina.

9. A process according to claim 7 in which the platinum group metal is platinum or palladium or a mixture thereof.

10. A process according to any one of the preceding claims in which
5 the composition of the hydrocarbon feed and the molecular oxygen-containing gas mixture comprises 2 to 20% of oxygen required for complete combustion to carbon dioxide and water.

11. A process according to any one of the preceding claims in which
10 the gas hourly velocity of the hydrocarbon feed is greater than 3000 hr⁻¹.

12. A process according to any one of the preceding claims wherein the process is operated at a temperature of 600-1200°C and under a pressure of 1-50 bar.

15


20


25

30

35

1 / 2





INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 93/01741

I. CLASSIFICATION OF SUBJECT MATTER (If several classification symbols apply, indicate all) ⁶		
According to International Patent Classification (IPC) or to both National Classification and IPC Int.Cl. 5 C10G11/22; C07C5/48		
II. FIELDS SEARCHED		
Minimum Documentation Searched ⁷		
Classification System	Classification Symbols	
Int.Cl. 5	C10G ; C07C	
Documentation Searched other than Minimum Documentation to the Extent that such Documents are Included in the Fields Searched ⁸		
III. DOCUMENTS CONSIDERED TO BE RELEVANT⁹		
Category ¹⁰	Citation of Document, ¹¹ with indication, where appropriate, of the relevant passages ¹²	Relevant to Claim No. ¹³
Y	EP,A,0 332 289 (BP) 13 September 1989 cited in the application see the whole document ----	1-12
Y	DE,A,2 723 685 (SIEMENS) 30 November 1978 see claims 1-12; figure 1 ----	1-12
A	FR,A,1 292 477 (CARL MERTENS) 2 June 1960 see claims 1-5; figures 1-3 ----	1-12
A	FR,A,1 113 102 (SAINTENOY) 28 November 1955 -----	
<p>¹⁰ Special categories of cited documents :¹⁰</p> <p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier document but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p> <p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step</p> <p>"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art</p> <p>"&" document member of the same patent family</p>		
IV. CERTIFICATION		
Date of the Actual Completion of the International Search 20 OCTOBER 1993		Date of Mailing of this International Search Report 29. 10. 93
International Searching Authority EUROPEAN PATENT OFFICE		Signature of Authorized Officer MICHIELS P.

**ANNEX TO THE INTERNATIONAL SEARCH REPORT
ON INTERNATIONAL PATENT APPLICATION NO.**

GB 9301741
SA 77887

This annex lists the patent family members relating to the patent documents cited in the above-mentioned international search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

20/10/93

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-0332289	13-09-89	AU-A- 2970489	14-09-89
		CA-A- 1316946	27-04-93
		JP-A- 1272534	31-10-89
		US-A- 4940826	10-07-90
		US-A- 5105052	14-04-92
DE-A-2723685	30-11-78	None	
FR-A-1292477		None	
FR-A-1113102		None	